

110083



BA-15, Mangolpuri Industrial area.



TESTING OF FOOD | WATER | CHEMICALS | TOYS | ELECTRONICS | BUILDING MATERIAL | ENVIRONMENT

## TEST CERTIFICATE

(This certificate is not valid without a hologram)

Sample : SBR Rubber Tile	Report No./ULR : 21000261 Version No. : 2		
Sample Description :SBR Rubber Tile-20mm			
Customer Ref : Nil, Dt-27/10/2018	Report Reissue Date: 12/11/2018		
Customer Name & Address :	Job Code	STRC/21000261	
Fab Flooring India	Sample Received On	30/10/2018	

Fab Flooring India (MANUFACTURERS & EXPORTERS OF RUBBER

FLOORING) T-4/2, Industrial Area, Phase- 1, Mangolpuri, Delhi -

Date of Testing Sample Quantity 30/10/2018 30/10/2018-12/11/2018 3 Piece of Sample

Sample Condition: --

S. No.	Test Parameters	Test Results	<b>Test Method</b>
1.	Tensile Strength (Mpa)	1.5	IS: 3400 (P-1) 2012
2.	% Elongation at break	120	IS: 3400 (P-1) 2012
3.	Density, kg/m³	980	IS: 3400 (P-9) 2014
4.	Specific Gravity	0.98	ASTM D 792-13
5.	Impact Resistance	No failure	ASTM D 1709-98
6.	Hardness , Shore A	62	ASTM D 2240-05
7.	Abrasion Resistance, % by weight	0.7	IS: 1237-2012
8.	Compression set, % 24 hour at 27±1°C	96.1	IS: 3400 (P-10) 1977
9.	Temperature Resistance test at -40°C	No Changes	STRC/STP/BM02
10.	Temperature Resistance test at 100°C	No Changes	STRC/STP/BM02
11.	Temperature Resistance test at 150°C	No Changes	STRC/STP/BM02

This Report replaces the Report No 21000261 Dated 05/11/2018 Note:

End of Report \*\*\*\*\*

Format No.: STRC/7.8/F/TC/Z/03



WWW.SIGMATEST.ORG

(1) The Test results listed refer only to tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.(2) Total liability of our Lab is limited to the invoiced amount. (3) Sample(s) are retained for 7 days (in case of perishable items) and 30 days for non perishable samples or unless otherwise specified. (4) This Test Report is not to be reproduced wholly or in part and cannot be used as an evidence in the court of Law and should not be used in any advertising media without our special permission in writing. (5) The Test Report refer to the sample submitted to us and not drawn by Sigma Test & Research Centre unless mentioned otherwise.